

Slip Check to AS 4586-2013 Stockmans Ridge Premium

Report Number: R19088a

Report Date: 25 July 2019

Total Number of Pages 2

Accredited for compliance with ISO/IEC 17025 – Testing

The results of the tests, calibrations and/or measurements included in this document are traceable to Australian/national standards

NATA is a signatory to the ILAC Mutual Recognition Arrangement for the mutual recognition of the equivalence of testing, medical testing, calibration and inspection reports


Issued by

Safe Environments Pty Ltd
Unit 4, 40 Bessemer Street
Blacktown NSW 2148

Prepared for

Australian Wood Company
Unit 6, 4-20 Violet Street
Revesby NSW 2212

Approved by



Dale Rowell
Authorised Signatory

25 July 2019

Test Report No. R19088a

Slip Resistance Classification of New Pedestrian Surface Materials

AS 4586-2013 Appendix A (Wet Pendulum Test)

The slip resistance classification has been determined for unused surfaces using specific conditions. Factors such as usage, cleaning systems, applied coatings and patterns of wear may affect the characteristics of the surface after classification. Standards Australia Handbook 198:2014 *Guide to the specification and testing of slip resistance of pedestrian surfaces* provides guidance for the selection of slip resistant pedestrian surfaces classified in accordance with AS 4586-2013. It is recommended that this test report be read in conjunction with AS 4586 and HB 198.

Requested by: Australian Wood Company
 Client Address: Unit 6, 4-20 Violet Street
 Revesby NSW 2212
 Product Manufacturer: Auswood
 Product Description: Stockmans Ridge Premium

Test conducted according to: AS 4586:2013 Appendix A
 Location: 4/40 Bessemer Street, Blacktown NSW 2148
 Conducted by: Kieran Mackowski

Date: 24 July 2019 Temperature: 17°C
 Sample: Unfixed Cleaning: None
 Rubber slider used: Slider 96 Conditioned: Grade P 400 paper dry followed
 Slope of specimen: Tested on a flat level surface by wet lapping film
 Direction of Test: NA

	Specimen 1	Specimen 2	Specimen 3	Specimen 4	Specimen 5
Mean BPN of last 3 swings:	37	41	37	38	37

Reported SRV of Sample:	38
Class:	P3

This test report shall not be reproduced unless in full, without written approval of Safe Environments Pty Ltd