

Specifications

envirobeam LVL E10



Name	envirobeam LVL E10
Standard	AS/NZS 4357.0:2005 (R2016)
Species	Mason Pine, Radiata pine
Veneer thickness	2.2mm
veneer joint	scarf
Adhesive	Phenol formaldehyde resins
Stress grade	E10
Density	550-700 kg/m ³
Mositure content	10-15%
Tolerances	-0/+4mm in thickness -0/+2mm in width/depth -0/+10mm in length

Stock and pack size

	70mm	90mm
35mm	150	120
45mm	120	96

Lengths	5.4m; 6m
Joint Capacity	JD3
Treatment	H2S
Surface	water resistant coating in brown color
Code	envirobeam LVL E10 H2S xxx 73 BENCHMARK BMP7xx0xx AS/NZS 4357.0 A-BOND E0